

## ILVA TECHNICAL DATA SHEET

**PRODUCT CODE:** TF 1525

**DESCRIPTION:** Haps Compliant Polyurethane Barrier Coat

**USES:** Barrier coat with isolating properties for exotic woods, improves substrates wetting. It must be used with polyester topcoats to prevent curing inhibition caused by some dyes and impurities found in MDF board.

<b>PRODUCT PREPARATION:</b>	<u>Parts by weight</u>	<u>Parts by volume (ounces)</u>
TF1525 Polyurethane Barrier Coat	100	128
TV19 Accelerator	5 - 10	8
TZ35NH Thinner	25	32

**APPLICATION SYSTEM:** Conventional or air-assisted airless spray

**QUANTITY:** 40 -60 gr sq mt per coat (1.6-2.4 wet mils)

**COATS:** One

<b>GENERAL PROPERTIES:</b> Specific Gravity, gr/cc	0.96 +/- 0.05
Viscosity*	10 +/- 2 sec
Application Viscosity* for spray	8 +/- 2 sec
Solids by Weight, %, as supplied	22 +/- 2
Solids by Weight, %, ready to use	17 +/- 2
Pot Life, hours at 20°C/68°F	4

\*ASTM D1200 (Ford) #4 at 20°C/68°F

<b>DRYING TIME:</b> (at 20°C/68°F)	Topcoating without sanding:	Minimum 2 hours Maximum 4 hours
	Sanding:	Must sand if not topcoated before 4 hours It is best to wait 8 hours before sanding.

**SHELF LIFE:** 18 Months

**STORAGE:** Store in a tightly closed container at room temperatures (18 -25 °C/64 -75 °F) and protect from moisture and foreign material.

**DATE OF ISSUANCE:** 06-05, Revised 12-13, 5-16, 10-17, 7-20, 12-20

IC & S, P.O. BOX 10845, LANCASTER, PA 17605  
(800) 220-4035

EVERY REASONABLE PRECAUTION IS TAKEN IN THE MANUFACTURE OF OUR PRODUCTS TO INSURE THAT THEY COMPLY WITH OUR STANDARDS. INFORMATION GIVEN IS CORRECT TO THE BEST OF OUR KNOWLEDGE. ANY SUGGESTIONS MADE BY US COVERING THE USE OF OUR PRODUCTS ARE BASED ON EXPERIENCE AND/OR TESTS BELIEVED TO BE RELIABLE. HOWEVER, BECAUSE THE USE OF ANY PRODUCT OF OUR MANUFACTURE IS COMPLETELY BEYOND OUR CONTROL, INCLUDING FOR EXAMPLE, THE METHOD AND CONDITIONS OF APPLICATION, NO GUARANTEE OR WARRANTY, EXPRESSED OR IMPLIED, IS MADE. MANUFACTURER'S MAXIMUM LIABILITY SHALL BE TO REPLACE SUCH QUANTITY OF PRODUCT DETERMINED BY OUR LABORATORY TO BE DEFECTIVE. USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR HIS INTENDED USE AND ASSUME ALL RISK AND LIABILITY IN CONNECTION THEREWITH.