

## ILVA TECHNICAL DATA SHEET

**PRODUCT CODE:** HMM5 Series

**DESCRIPTION:** WB CLEAR SELF-SEALER VARIOUS SHEENS

**USES:** Furniture, architectural millwork, store fixtures. Offers the best in dry times and leveling, with very good sanding properties and filling power.

**PRODUCT PREPARATION:** HMM5 Series      WB Clear Self-Sealer      100 parts by weight      128 parts by volume  
Water      Thinner      0-5 parts by weight      0-6 parts by volume

**APPLICATION SYSTEM:** Spray

**FILM THICKNESS:** 4.4-5.6 mils wet

**COATS:** Two

**GENERAL PROPERTIES:** Specific Gravity, gr/cc      1.040 +/- 0.02  
Viscosity -- Iso 6 cup      85+/- 5 secs  
Solids by Weight, %, as supplied      33 +/- 2 sec  
Thinner      Water  
Dilution      0-5%

**DRYING TIME:** All dry times are dependent upon air flow, ambient temperatures, and humidity  
(at 20°C/68°F) Drying time at room temperature      2-3 hr  
Drying time with warm air tunnel      20-30 mins  
Dust Free/time gel      30-60 mins  
Dry to Touch      2-3 hr  
Dry hard      6-8 hr  
Stackable      overnight  
Sandable      after 2-3 hrs, before applying topcoat

**GLOSS LEVELS:** HMM5036      10 SHEEN  
HMM5034      20 SHEEN  
HMM5033      30 SHEEN  
HMM5032      50 SHEEN  
HMM5031      60 SHEEN

**SHELF LIFE:** 12 Months

**STORAGE:** Store in a tightly closed container at room temperatures (18-25°C/64-75°F) and protect from moisture and foreign material. Do not store at temperatures below 7°C (45°F)

**DATE OF ISSUANCE:** 1-15, 3-17, 11-18, 5-19

**IC & S, P.O. BOX 10845, LANCASTER, PA 17605  
(800) 220-4035**

EVERY REASONABLE PRECAUTION IS TAKEN IN THE MANUFACTURE OF OUR PRODUCTS TO INSURE THAT THEY COMPLY WITH OUR STANDARDS. INFORMATION GIVEN IS CORRECT TO THE BEST OF OUR KNOWLEDGE. ANY SUGGESTIONS MADE BY US COVERING THE USE OF OUR PRODUCTS ARE BASED ON EXPERIENCE AND/OR TESTS BELIEVED TO BE RELIABLE. HOWEVER, BECAUSE THE USE OF ANY PRODUCT OF OUR MANUFACTURE IS COMPLETELY BEYOND OUR CONTROL, INCLUDING FOR EXAMPLE, THE METHOD AND CONDITIONS OF APPLICATION, NO GUARANTEE OR WARRANTY, EXPRESSED OR IMPLIED, IS MADE. MANUFACTURER'S MAXIMUM LIABILITY SHALL BE TO REPLACE SUCH QUANTITY OF PRODUCT DETERMINED BY OUR LABORATORY TO BE DEFECTIVE. USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR HIS INTENDED USE AND ASSUME ALL RISK AND LIABILITY IN CONNECTION THEREWITH.